

**Product 02660000** 2-comp. Polyurea sealer, UV- and colour stable, transparent, glossy

### 1 General Data

#### Fields of application

VIASOL UREA S6600 is used as UV- and colour-stable, transparent seal coat for coating systems broadcasted with coloured quartz sand based on polyurethane or epoxy resin. VIASOL UREA S6600 can be used for indoor and outdoor application and cures with a glossy finish.

#### Product Description

VIASOL UREA S6600 is a low emission, solvent free, low temperature, UV- and colour-stable 2 component seal coat based on aliphatic Polyurea resin. In the cured state the product has a very good abrasion resistance, excellent weathering and UV stability, is characterized by the properties of a tough-hard surface. Exposure to chemicals may lead to optical discoloration that will not affect the technical usability of the flooring (see chemical resistance list). VIASOL UREA S6600 has a low susceptibility to pollution and is easy to clean.

#### Properties

- solvent free
- low emissions tested according to AgBB
- UV- and colour-stable, no yellowing
- fast and low temperature curing
- abrasion resistant
- glossy

#### VIASOL systems

VIASOL UREA S6600 is an optional seal coat for the following VIASOL systems:

- VIASOL **DESIGN QCV**
- VIASOL **DESIGN QCV conductive**
- VIASOL **DESIGN QNV**

#### Care and maintenance

For a long-term preservation of the properties of resin floors, we recommend a regular cleaning and care programme. For further details see our VIASOL Care and Maintenance Guide. Before first use we recommend to perform a basic cleaning and initial care.

#### Technical support

For system build up possibilities and detailed information relating to the laying of VIASOL products, please refer to the VIASOL System Planner or contact VIACOR Polymer GmbH directly.

Phone: +49 (0)7472-949990  
E-Mail: [info@viacor.de](mailto:info@viacor.de)

#### Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg, Tel: +49 7472 94999-0, [info@viacor.de](mailto:info@viacor.de), [www.viacor.de](http://www.viacor.de)

#### (A) Technical Data

##### Liquid mixture (A+B)

1.	Solids content	> 99%
2.	Viscosity (23 °C)	ca. 900 - 1200 mPas
3.	Density (20 °C)	ca. 1.1 g/cm <sup>3</sup>
4.	Packaging size (2-component container)	18 kg (10.6 kg A + 7.4 kg B)
5.	Colour	Transparent
6.	Shelf life (20 °C)	12 months in originally closed container
7.	Storage	Dry at 10-25°C, avoid direct sunlight, protect from freezing

#### (B) Technical Data

##### Cured material

1.	Adhesive strength (EN ISO 4624)	> 2.0 N/mm <sup>2</sup>
1.	Hardness Shore-D (EN ISO 868)	D78
2.	Wear resistance EN ISO 5470-1	64 mg (Taber CS17) 220 mg (Taber H22)



Tested in system: VIASOL **DESIGN**

**Product 02660000** 2-comp. Polyurea sealer, UV- and colour stable, transparent, glossy

## 2 Application Method

Please refer also to our general application guideline and the application guideline of VIASOL DESIGN systems.

### Substrate preparation

The substrate must be clean and free of dust and loose particles. All traces of contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance should be removed.

VIASOL UREA S6600 is applied on VIASOL EP- or PU wear coats broadcasted with colored quartz sand or other suitable materials.

VIASOL UREA S6600 can be applied after the waiting time for overcoating mentioned in the specific product data sheet of the previous layer is over.

### Application

The product is supplied in matched quantities in 2-component containers. The B component must be completely emptied into the A component (stir component A previously). Both components should be mixed homogeneously with a suitable electric stirrer for at least 2-3 minutes and then the mixture should be poured in another container and mixed again for about 1 minute. The mixing in of air should be avoided. We recommend the application by equal batch numbers.

VIASOL UREA S6600 is poured onto the surface to be sealed and spread evenly over the surface with a rubber squeegee (hard or soft) or a rubber trowel. Formation of puddles and scratch marks has to be avoided. If necessary, immediately after application rolling with a short pile microfibre roller (for example Multitool microfibre 6 or 8 mm) in one direction as far as possible without stops in the lane. The processing time at 20 ° C and 50% rel. humidity is at room temperature at max. 3 - 5 minutes. Higher temperatures and higher humidity shorten the processing time. Later rolling can cause fine air bubbles in the surface.

The product can be applied in several layers.

**NOTE:** The roller should be replaced after 30 minutes, otherwise microbubbles and roller tracks may appear on the floor caused by cured material the roll.

For cleaning of tools and other dirt VIASOL SO-X12 cleaner is recommended.

### Over coating

Over coating within 18 hours after application, the latest layer must not be grinded. If you applicate after 18h, exact grinding is necessary.

### Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg, Tel: +49 7472 94999-0, [info@viacor.de](mailto:info@viacor.de), [www.viacor.de](http://www.viacor.de)

### (B) Technical Data

#### Liquid mixture (A+B)

1. Mixing ratio A : B	100 : 70 (% by weight)
2. Material consumption on smooth surface on spreaded surface (1 <sup>st</sup> time) on spreaded surface (2 <sup>nd</sup> time)	600 – 800 g/ m <sup>2</sup> 400 – 700 g/m <sup>2</sup> 100 – 300 g/m <sup>2</sup>
3. Working time (20 °C) Drying time for seams during application (20°C)	approx. 20 minutes max. 10 minutes
4. Application temperature	10 – 30 °C (min. 3°C above dew point)
5. Relative humidity	40 to max. 85%
6. Foot traffic 10°C 15°C 20°C	approx. 24h approx. 16-24h approx. 12-16h
7. Following layer (20°C)	within 18 hours °
8. Fully capable of with-standing stress mechanical (20 °C) chemical (20 °C)	after 3 days after 7 days

° Please note that for a two-layer installation, the subsequent coating must be completed within 18 hours! The best way to achieve a 2-layer processing in one day (at temperatures of 20°C and a relative humidity of 50%)

Product 02660000 2-comp. Polyurea sealer, UV- and colour stable, transparent, glossy

### 3 Further Information

#### CE-Mark



##### CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and declaration of performance.

#### Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product Category IIA j Type Lb products (in the ready to use state) is:

Stage II (from 2010) < 500 g/l VOC

In the ready to use state, this product contains less than 500 g/l VOC.

#### Hazard notes

**GIS-Code: PU 60**

Hazardous Substances Ordinance: Labelling obligation

#### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

#### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and  
-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all VIACOR data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see [www.viacor.de](http://www.viacor.de) or contact us directly).

#### Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg, Tel: +49 7472 94999-0, [info@viacor.de](mailto:info@viacor.de), [www.viacor.de](http://www.viacor.de)