PORPLASTIC M olympic

Massive, One or Multilayer Full PU-Bound System spread with Coloured EPDM Granules, Water-Impermeable

PROFESSIONAL SPORTS SURFCE

Low emission

Porplastic







WA certified





Application fields

Running tracks Run up	tracks short distance tracks			
athletic sport areas type A	, B, C High-performance sport			
International competitions Olympia, world championships				

VIACOR Polymer GmbH Graf-Bentzel-Str. 78 72108 Rottenburg Tel. 07472 94 999-0 Fax 07472 94 999-39 info@viacor.de www.viacor.de

Application and Consumption

LAYER		<u>Consumption</u>	<u>thickness</u>	<u>Application</u>
LINE PAINT PORPLASTIC X8090		20 – 30 g/lfm	ca. 0,1 – 0,2 mm	Spray
UV-SEALER (optional) PORPLASTIC S6020	\$	0,17 – 0,2 per layer	ca 0,1 mm	Spray, In 2 layers
WEARING LAYER PORPLASTIC C570 PORPLASTIC EPDM (1-4mm)		ca. 2,8 kg/m² 2,8 net 4,0 total	ca. 3 - 5 mm	Notched squeegee, broadcast, remove excess
2. CAST COATING PORPLASTIC C570 PORPLASTIC SBR (1-4mm)	\$	ca. 3 kg/m² 3,0 net 3,5 total	ca. 5 mm	Notched squeegee, broadcast, remove excess
1. CAST COATING PORPLASTIC C570 PORPLASTIC SBR (1-4mm)		3 - 3,5 kg/m² 3,0 net 3,5 total	ca. 5 mm	Notched squeegee, broadcast, remove excess
PRIMER PORPLASTIC P270 (for asphalt)	\$	0,15 – 0,2 kg/m²	0,1 mm	Roll or spray

Performance-Check



Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore no liability claims can be derived from the system data sheet. As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.de or contact us directly). Date of issue: January 2024 - all technical information is subject to change without prior notice







Manufacturer: